

DCP DATA SHEET

Project:
 Location:
 Depth of zero point below surface:
 Material Classification:
 Pavement conditions:

Date:
 Personnel:
 Hammer Weight:
 Weather:
 Water Table Depth:

#	(1) Number of Blows	(2) Cumulative Penetration (mm)	(3) Penetration Between Reading (mm)	(4) Penetration per Blow (mm)	(5) Hammer Blow Factor	(6) DCP Index mm/blow	(7) CBR %	(8) Moisture %
1								
2								
3								
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								

- | | |
|---|--|
| <p>(1) Number of hammer blows between test readings</p> <p>(2) Cumulative penetration after each set of hammer blows</p> <p>(3) Difference in cumulative penetration (2) between readings</p> <p>(4) (3) divided by (1)</p> | <p>(5) Enter 1 for 8-Kg (17.6-lb) hammer; 2 for 4.6-Kg (10.1-lb) hammer</p> <p>(6) (4) x (5)</p> <p>(7) From CBR versus DCP Index correlation</p> <p>(8) % Moisture content when available</p> |
|---|--|

